



# Type EW-R-PP-LS



#### Product information

- simple, lightweight version for the installation of pre-assembled cables
- flexible conduit for simple dynamic applications
- medium mechanical load
- resource-saving through recycled material
- for mechanical engineering and chemical plants

## Information, conformities and approvals











Article	Order No.	Color	UV	metric	PG	NW	A Ø mm	B Ø mm	Stat./Dyn. Radius mm	Weight kg/100m	PU m
EW-R-PP-LS 06	83201402	Black	✓				6.4	9.8	14/60	1.5	100
EW-R-PP-LS M10/P07	83201406	Black	✓	M10	PG07	NW 7	8.3	11.5	21/70	1.6	100
EW-R-PP-LS M12/P09	83201408	Black	✓	M12	PG09	NW 10	9.9	12.9	26/80	2.0	100
EW-R-PP-LS M16/P11	83201410	Black	✓	M16	PG11	NW 12	12.1	15.7	33/100	2.8	100
EW-R-PP-LS M20/P16	83201416	Black	✓	M20	PG16	NW 17	15.6	21	46/180	4.2	100
EW-R-PP-LS M25/P21	83201420	Black	✓	M25	PG21	NW 23	22.3	28.3	59/230	7.0	100
EW-R-PP-LS M32/P29	83201426	Black	✓	M32	PG29	NW 29	28	34.3	70/280	9.0	50
EW-R-PP-LS M40/P36	83201430	Black	✓	M40	PG36	NW 36	34.9	42.1	86/310	12.5	25
EW-R-PP-LS M50/P48	83201434	Black	✓	M50	PG48	NW 48	46.9	54	107/350	17.4	25

#### Material properties



Polypropylene (PP)

© Murrplastik Systemtechnik GmbH • 1 as of 2025-03-22 - 182547





# Type EW-R-PP-LS

## Material properties



High angle consistency>210 N >350 N50 x 50 mm 100 x 100 mm According to IEC EN 61386 According to IEC EN 61386 M25/P21 Testing at 23  $^{\circ}\text{C}$  Testing at 23  $^{\circ}\text{C}$ 



Flexural fatigue strength>1000000 ~According to IEC EN 61386 M25/P21 Testing at -45  $^{\circ}\mathrm{C}$ 



Impact strength4.5 According to IEC EN 61386 M25/P21 Testing at -25 °C



System tear-out strength>360 NAccording to IEC EN 61386 M25/P21 Testing at 23  $^{\circ}\text{C}$  Fitting SVT

#### Thermal properties



Temperature / temperature range -40 °C - 130 °C

#### Fire properties



Fire classificationacc. to UL94: HB

### Chemical resistances



Resistant to:Alcohol Greases Fuels Lyes Mineral oils Weak acids

#### Technical information



Halogen-free



UV-resistant acc. to ISO 4892-2

### Conformity



RoHS (EC Directive 2011/65/EU)

#### Approvals and operating permits



ECOLAB approval





# Type EW-R-PP-LS

#### Classification



ETIM 9: EC001175 ECLASS 14: 27430305

#### **General information**



Made in Germany

All details given in our sales brochures and catalogues, as well as the information available online, are based on our current knowledge of the products described.

The electronic data and files made available by Murrplastik, particularly CAD files are based on our current knowledge of the product described.

A legally binding assurance of certain properties or the suitability for a certain purpose can not be determined from this information.

All information with respect to the chemical and physical properties of Murrplastik products, as well as application advice given verbally, in writing or by tests, is given to the best of our knowledge. They do not release the buyer from the obligation to carry out his own tests and trials in order to determine the concrete suitability of the products for the intended purpose.

Murrplastik accepts no responsibility for the available information being up-to-date, correct or complete. Neither do we accept responsibility for the quality of this information.

Murrplastik reserves the right to make technical changes and improvements through constant further development of products and services.

Our General Terms and Conditions apply.