



Type GF-P-LS



Product information

The self-retracting fabric conduit with longitudinal slot provides excellent mechanical protection against abrasion for your lines. First off it prevents rattling even better, plus it can be installed at any place and at any time.

Additional advantages of the GF-P-LS braided conduit include:

High mechanical protection

- Light-weight / low mass
- High flexibility
- Great chemical resistance
- Flame resistant

Information, conformities and approvals



Article	Order No.	Color	UV	Nominal width NW	Size range mm	Weight kg/100m	PU m
GF-P-LS-5	83342110	Black	✓	5	3 / 5	1.71	25
GF-P-LS-8	83342112	Black	✓	8	5 / 8	2.12	25
GF-P-LS-10	83342114	Black	✓	10	8 / 10	2.43	25
GF-P-LS-13	83342116	Black	✓	13	10 / 13	2.54	25
GF-P-LS-16	83342118	Black	✓	16	13 / 16	3.38	25
GF-P-LS-19	83342120	Black	✓	19	16 / 19	3.38	25
GF-P-LS-25 1)	83342122	Black	✓	25	22 / 25	4.81	25
GF-P-LS-29	83342124	Black	✓	29	26 / 29	5.18	25
GF-P-LS-32	83342126	Black	✓	32	29 / 32	6.35	25
GF-P-LS-38	83342128	Black	✓	38	32 / 44	7.56	25
GF-P-LS-50	83342130	Black	✓	50	44 / 50	7.56	25

1) No stock goods, delivery time and minimum order quantities upon request

1) No stock goods, delivery time and minimum order quantities upon request



Type GF-P-LS

Material properties



mod. polyester

Thermal properties



Temperature / temperature range

-55 °C - 150 °C / short term: 175 °C

Fire properties



Fire classification

UL 224 / FMV SS302 self-extinguishing type B



Fire properties as per EN 45545-2

C.I.T. R22 / R23 HL3 :0,11 NF X 70-100-1/-2 600°C (1112 °F)

LOI R22 / R23 HL3 :34.0 ISO 4589-2

Ds (max.) R22 HL2 / R23 HL3 :213 ISO 5659-2 (25 kW/m²)

Chemical resistances



Resistant to:

Mineral oils
Fuels

Technical information



Halogen-free

Conformity



RoHS (EC Directive 2011/65/EU)

Approvals and operating permits



EU railway approval

Classification

ETIM 9: EC001182

ECLASS 14: 27430303

UNSPSC 26.0801: 40183009

All details given in our sales brochures and catalogues, as well as the information available online, are based on our current knowledge of the products described.

The electronic data and files made available by Murrplastik, particularly CAD files are based on our current knowledge of the product described.

A legally binding assurance of certain properties or the suitability for a certain purpose can not be determined from this information.

All information with respect to the chemical and physical properties of Murrplastik products, as well as application advice given verbally, in writing or by tests, is given to the best of our knowledge.

They do not release the buyer from the obligation to carry out his own tests and trials in order to determine the concrete suitability of the products for the intended purpose.

Murrplastik accepts no responsibility for the available information being up-to-date, correct or complete. Neither do we accept responsibility for the quality of this information.

Murrplastik accepts no liability for damage caused as a result of using our products.

Murrplastik reserves the right to make technical changes and improvements through constant further development of products and services.

Our General Terms and Conditions apply.