



Type EWX-PAE-LS (high corrugation)




Product information

The EWX-PAE-LS cable protection conduits are made of specially modified polyamide 12. The material is halogen, phosphor and cadmium-free. With its excellent flexural fatigue strength, this product is ideal for robotics engineering and in the area of handling systems. For installation of pre-assembled cables, retrofitting or repair of cables. For dynamic applications involving light to medium mechanical loads.

The EWX-PAE-LS cable protection conduits have a higher corrugation and feature the following advantages:

- Very good flexibility
- Excellent flexural fatigue strength
- Less wear
- Good crush resistance
- Subsequent installation possible





Information, conformities and approvals













Article	Order No.	Color	UV	metric	PG	NW	A Ø mm	B Ø mm	Stat./Dyn. Radius mm	Weight kg/100m	PU m
EWX-PAE-LS- M20/P16	83182256	Black	✓	M20	PG16	NW 17	13.3	21.1	36/77	6.0	50
EWX-PAE-LS- M25/P21	83182258	Black	✓	M25	PG21	NW 23	19.2	28.2	49/104	11.0	50
EWX-PAE-LS- M32/P29	83182260	Black	✓	M32	PG29	NW 29	23.1	34.5	57/117	14.0	25
EWX-PAE-LS- M40/P36	83182262	Black	✓	M40	PG36	NW 36	28.5	42.2	71/146	18.2	25
EWX-PAE-LS- M50/P48	83182264	Black	✓	M50	PG48	NW 48	36.5	53.6	87/167	24.0	25
EWX-PAE-LS-56 Jumbo	83182278	Black	✓			NW 56	51.7	67.7	95/220	40.0	25
EWX-PAE-LS-70 Jumbo	83182280	Black	✓			NW 70	64.3	80.3	115/235	52.0	25

Material properties



mod. polyamide PA 12



High angle consistency>340 N >570 N50 x 50 mm 100 x 100 mm According to IEC EN 61386 According to IEC EN 61386 M25/P21 M25/P21 Testing at 23 °C Testing at 23 °C





Type EWX-PAE-LS (high corrugation)

Material properties



Flexural fatigue strength>5000000 ~According to IEC EN 61386 M25/P21 Testing at $-45\,^{\circ}\mathrm{C}$



Impact strength4 According to IEC EN 61386 M25/P21 Testing at -25 $^{\circ}$ C



System tear-out strength>420 NAccording to IEC EN 61386 M25/P21 Testing at 23 $^{\circ}\text{C}$ Fitting SVT/X

Thermal properties



Temperature / temperature range -40 °C - 120 °C / short term: 150 °C

Fire properties



Fire classificationacc. to UL94: HB

Chemical resistances



Resistant to:Alcohol Greases Fuels Lyes Mineral oils

Weak acids

Technical information



Halogen-free



UV-resistant acc. to ISO 4892-2

Conformity



RoHS (EC Directive 2011/65/EU)

Approvals and operating permits



ROBI approval



ECOLAB approval





Type EWX-PAE-LS (high corrugation)

Classification



ETIM 9: EC001175 ECLASS 14: 27430305 UNSPSC 26.0801: 39131601

General information



Made in Germany