




## Type EWX-PAE (high corrugation)



### Product information

The EWX-PAE cable protection conduits are made of specially modified polyamide 12. The material is halogen, phosphor and cadmium-free. With its excellent flexural fatigue strength, this product is ideal for robotics engineering and in the area of handling systems. For extremely dynamic applications involving medium to high mechanical loads.

The EWX-PAE cable protection conduits have a higher corrugation and feature the following advantages:

- Very good flexibility
- Excellent flexural fatigue strength
- Less wear
- Good crush resistance

### Information, conformities and approvals



Article	Order No.	Color	UV	metric	PG	NW	A Ø mm	B Ø mm	Stat./Dyn. Radius mm	Weight kg/100m	PU m
EWX-PAE M20/ P16 1**)	83182056	Black	✓	M20	PG16	NW 17	13.3	21	40/80	6.0	50
EWX-PAE-M25/ P21	83182058	Black	✓	M25	PG21	NW 23	18.3	28	49/104	11.0	50
EWX-PAE-M32/ P29	83182060	Black	✓	M32	PG29	NW 29	23.1	34.5	57/117	12.0	25
EWX-PAE-M40/ P36	83182062	Black	✓	M40	PG36	NW 36	28.5	42.2	71/146	18.2	25
EWX-PAE-M50/ P48	83182064	Black	✓	M50	PG48	NW 48	36.7	53.5	87/167	24.0	25
EWX-PAE-56 Jumbo	83182078	Black	✓			NW 56	52.2	67.7	95/220	40.0	25
EWX-PAE-70 Jumbo	83182080	Black	✓			NW 70	64	80.3	115/235	52.0	25
EWX-PAE-70 Jumbo	83182084	Black	✗			NW 70	64	80.3	115/235	52.0	110
EWX-PAE-80 Jumbo	83182081	Black	✗			NW 80	76	92.8	195/380	66.0	15
EWX-PAE-95 Jumbo	83182082	Black	✗			NW 95	88.2	105.5	220/450	82.0	10
EWX-PAE-M25/ P21 1)**)	83182018	Gray	✗	M25	PG21	NW 23	18.3	28	49/104	11.0	50
EWX-PAE-M32/ P29 1)	83182020	Gray	✗	M32	PG29	NW 29	23.1	34.5	57/117	12.0	25
EWX-PAE-M40/ P36	83182022	Gray	✗	M40	PG36	NW 36	28.5	42.2	71/146	18.2	25



## Type EWX-PAE (high corrugation)

Article	Order No.	Color	UV	metric	PG	NW	A Ø mm	B Ø mm	Stat./Dyn. Radius mm	Weight kg/100m	PU m
---------	-----------	-------	----	--------	----	----	-----------	-----------	----------------------------	-------------------	------

1)\*\*)

1) Discontinued product!

1\*\*) No stock goods, delivery time and minimum order quantities upon request

1) Discontinued product!

1\*\*) No stock goods, delivery time and minimum order quantities upon request

### Material properties

	mod. polyamide PA 12
	High angle consistency
	>490 N 50 x 50 mm According to IEC EN 61386 M25/P21 Testing at 23 °C
	>940 N 100 x 100 mm According to IEC EN 61386 M25/P21 Testing at 23 °C
	Flexural fatigue strength
	>5000000 Cycles According to IEC EN 61386 M25/P21 Testing at -45 °C
	Impact strength
	4 According to IEC EN 61386 M25/P21 Testing at -25 °C
	System tear-out strength
	>170 N According to IEC EN 61386 M25/P21 Testing at 23 °C Fitting M-PRO

### Thermal properties

	Temperature / temperature range
	-40 °C - 120 °C / short term: 150 °C

### Fire properties

	Fire classification
	acc. to UL94: HB

### Chemical resistances

	Resistant to:
	Alcohol
	Greases
	Fuels
	Lyes
	Mineral oils
	Weak acids



## Type EWX-PAE (high corrugation)

### Technical information

	Halogen-free
	UV-resistant acc. to ISO 4892-2

### Approvals and operating permits

	ROBI approval
	ECOLAB approval

### Classification

ETIM 9: EC001175
ECCLASS 14: 27430305

### General information

	Made in Germany
------------------------------------------------------------------------------------	-----------------

All details given in our sales brochures and catalogues, as well as the information available online, are based on our current knowledge of the products described. The electronic data and files made available by Murrplastik, particularly CAD files are based on our current knowledge of the product described. A legally binding assurance of certain properties or the suitability for a certain purpose can not be determined from this information. All information with respect to the chemical and physical properties of Murrplastik products, as well as application advice given verbally, in writing or by tests, is given to the best of our knowledge. They do not release the buyer from the obligation to carry out his own tests and trials in order to determine the concrete suitability of the products for the intended purpose. Murrplastik accepts no responsibility for the available information being up-to-date, correct or complete. Neither do we accept responsibility for the quality of this information. Murrplastik accepts no liability for damage caused as a result of using our products. Murrplastik reserves the right to make technical changes and improvements through constant further development of products and services. Our General Terms and Conditions apply.